

Blacktop Crack Filler

Asphalt Emulsion Formula



Manufacturer:

ThorWorks Industries, Inc.
2520 S. Campbell St.
Sandusky, OH 44870
Phone: 800-326-1994
Fax: 419-626-5477

Description

Asphalt emulsion crack filler designed for filling cracks in asphalt pavement.

Uses

Asphalt (blacktop) driveways & walkways.

Coverage

Dependent upon depth and width of crack.

Directions

SURFACE PREPARATION: Surface must be cleaned of dirt, dust and debris for proper adhesion.

APPLICATION: Cut tip of spout to desired width and puncture seal. Apply material into crack with caulking gun. Allow to dry for 24 hours before applying driveway sealer.

Clean Up

Wash tools with water before material dries.

Drying Time

Allow Crack Filler to cure for 24-48 hours prior to sealing or opening to traffic.

Important

Read entire label before using. Application temperature must be a minimum of 60 °F and rising. Do not apply when temperature is expected to drop below 60 °F within a 24 hour period. Be sure to wear eye protection, gloves, long pants, and long sleeves when mixing and applying SealBest materials. In areas where dew or fog accumulates in the early evening, it is best to coat in the morning. Stop coating by early afternoon (3:00 pm) to prevent wash off, which will occur if dew, fog, or rain arrive before coating dries. Do not apply if rain is imminent or forecast within 24 hours of application. **DO NOT USE ON CONCRETE SURFACES.**

Precautions

- Do Not Heat Or Thin
- Do Not Freeze
- Do Not Store At Temperatures Below 50 °F

Safety And Environmental Precautions

- Refer To Material Safety Data Sheet Before Using
- For Exterior Application Only
- Apply In A Well Ventilated Area
- Close Container When Not In Use
- Environmental Information Is On The Material Safety Data Sheet
- Do Not Reuse Empty Container
- Volatile Organic Content (VOC) Is 10 Gm/Liter Max
- Keep Out Of Reach Of Children
- Avoid Breathing Vapors And Contact With Eyes And Skin. Do Not Take Internally
- Wear Eye Protection And Gloves When Applying

| Ingredients: | CAS No. |
|---------------|-------------|
| Asphalt | 8052-42-4 |
| Clay | 1332-58-7 |
| Polymer Latex | Proprietary |
| Water | 7732-18-5 |

Blacktop Crack Filler

Revised: 01/11